

TECHNICAL DATA SHEET

LCS

Travertino Romano Finitura

Technical characteristic

sec. 1

TRAVERTINO ROMANO FINITURA by OIKOS is a semitransparent paint for interiors and exteriors that has been created to protect the decoration of TRAVERTINO ROMANO. It has an extremely high yield and allows the applicator to highlight the shades and tones of the veins of natural stone. The product can be coloured using the special TONER to obtain all the colours of the color chart. It is odourless, not toxic, not flammable, harmless to the environment and the human life.

Ideal use

sec. 2

As finishing for TRAVERTINO ROMANO by OIKOS

Application method

sec. 4

Wait until TRAVERTINO ROMANO by OIKOS is completely dry.

TRAVERTINO ROMANO naturale

To protect and maintain the natural effect of TRAVERTINO ROMANO, apply by brush, a coat of undiluted, uncoloured TRAVERTINO ROMANO FINITURA.

TRAVERTINO with a colour finish

Apply by brush a coat of undiluted and uncoloured TRAVERTINO ROMANO FINITURA, paying attention to only spread the product on the smooth parts of the surface and not inside the dimpled areas that recreate the veins of natural stone. Wait until the first coat of the finitura is dry and then proceed to apply by brush, a second coat of TRAVERTINO ROMANO FINITURA in the chosen colour, diluting the product first with 50% water. Remove excess product using a sponge so as to achieve the light dark effect caused by the different levels of absorption of the surface between the smooth areas and the dimpled ones

sez. 5.0 Finish

To obtain the desired shade of the colour chart, mix 100 ml of TONER with 1lt of TRAVERTINO ROMANO FINITURA and mix thoroughly.

Technical characteristics: the application

sec. 6

Dilution/Mixing	1st coat: ready to use, 2nd coat 50%
Yield	1st coat 15 ÷ 20 m ² /l, 2nd coat 40 ÷ 50 m ² /l
Application tools	Brush, Synthetic sponge by OIKOS
Base coat	TRAVERTINO ROMANO by OIKOS
Application temperature	+5°C ÷ +36°C (with relative humidity not exceeding 80%)
Drying time: touch dry	1 ÷ 2 h (temperature = 20°C with relative humidity at 75%)
Drying time until washable	30 days (temperature = 20°C with relative humidity at 75%)
Drying time: fully cured	6 ÷ 8 h (temperature = 20°C with relative humidity at 75%)
Tools cleaning	Water
Warning	Protect the surface from the rain for the first 48÷ 72 hours after application.

Technical characteristics: the product

sec. 7

Composition	Binders in water dispersion, high coverage fillers, titanium dioxide based pigments, organic and inorganic pigments, preservatives and additive to facilitate application and formation of the surface film.
Specific weight	1,2 kg/l +/- 3%
pH	8.5 ÷ 10
Viscosity	3000 - 5000 CPS Brookfield (RVT 20 revs/min. a 25°C)
Storage temperature	+2°C ÷ +36°C. Keep from freezing
Reaction to fire	Negative if the product is applied on to a non inflammable base; water based material with a dry thickness

Technical data sheet LCS/tf/01

	of less than 0,600 mm
Water absorption:	W24 TRAVERTINO CYCLE: Coefficient of water absorption at 24 hours (UNI EN 1062-3:2001) = 0.144 kg/m ² /(t*1/2)
Permeability to water vapour Sd	(UNI EN ISO 7783-2): high, Sd=0.008 m, μ=74,76
Colours	Shades of the colour chart
Packaging	1 0,5 – 1 – 4
Texture	Travertino

Toxicological data

sec. 8

The product is free of any harmful substances, pigments or other components containing heavy metals such as lead or chrome. Further to this, the product contains no toxic solvents, aromatics or chlorides. There is no risk of any dangerous polymerisation. The product is non combustible and is held to be a non-toxic substance if used in the technically correct manner. Normal cautionary measures for the handling of water based paints are advised. No special arrangements are required for the storage, movement and transportation of the product, any spillage should be cleaned up using absorbent inert material such as sand, soil etc. etc. and then disposed of as any normal waste product according to national and regional current regulations. The transportation must be carried out in conformity with international agreements.

Specifications

sec. 9

The surface should be thoroughly dry. Apply a first coat of ready to use FINITURA on TRAVERTINO ROMANO by OIKOS, wait four hours until dry and then proceed to apply a second coat of FINITURA diluted 50% in the chosen colour. Remove any excess product using a sponge. All should be carried out in respect of the standard norms for application, with a cost of al m² including material and labour.